

COMPARISON OF GAUGES

Gauge	United States Std.	USS Rev.	Thickness Equivalent Galv. Sheet	Brown and Sharpe	Oz./ Sq. Ft.	Decimal Equivalent
	Stainless Steel Monel Nickel	Galvannealed Cold Rolled Hot Rolled Steel Sheet	After Galvanizing	Aluminum Brass Bronze		Copper
30	.0125	.0120	.0157	.0100	8	.0108
29	.0140	.0135	.0172	.0113	—	—
28	.0156	.0149	.0187	.0126	10	.0135
26	.0187	.0179	.0217	.0159	14	.0189
24	.0250	.0239	.0276	.0201	18	.0243
22	.0312	.0299	.0336	.0253	—	—
20	.0375	.0359	.0396	.0320	28	.0377
18	.0500	.0478	.0516	.0403	—	—
16	.0625	.0598	.0635	.0508	40	.0539
14	.0781	.0747	.0785	.0641	64	.0863
13	.0937	.0897	.0934	.0720	3/32	.0937
12	.1093	.1046	.1084	.0808	—	—
11	.1250	.1196	.1233	.0907	1/8	.1250
10	.1406	.1345	.1382	.1019	—	—
7	.1875	.1793	—	.1443	—	—
3	.2500	.2391	—	.2294	—	—

